



## Reflection™ – 38/40

Density	38kg/m <sup>3</sup> – 39kg/m <sup>3</sup>
Hardness (IFD 25%)	35N +/- 10
(IFD 40%)	40N +/- 10
(IFD 65%)	75N +/- 10
Porosity	15 L/m
Tear Resistance	200N Minimum
Tensile	70 kPa Minimum
Elongation	200% Minimum
Resilience	10% Minimum
Compression Set	15% Maximum
Indentation (Sag) Factor	1.85% min
Standard Colour	White

### Testing standards

All foams comply with AS2281-1993

All foams are tested to AS2282-1993

### Typical Applications:

Pillows, mattress and seat overlays, quilting

### Warranty:

Domestic application: 10 year warranty

Commercial application: 7 year warranty

#### MELBOURNE

81 Castro Way, Derrimut, VIC 3030  
P 03 9308 7007 F 03 9308 7008  
E [foamordersvic@foamco.com.au](mailto:foamordersvic@foamco.com.au)

#### BRISBANE

817 Beaudesert Road, Coopers Plains, QLD  
P 07 3848 0078 F 07 3848 0079  
E [foamordersqld@foamco.com.au](mailto:foamordersqld@foamco.com.au)

#### PERTH

P 02 8796 9500  
E [foamorders@foamco.com.au](mailto:foamorders@foamco.com.au)

#### ADELAIDE AND TASMANIA

P 03 9308 7007  
E [foamorders@foamco.com.au](mailto:foamorders@foamco.com.au)  
E [foaminfo@foamco.com.au](mailto:foaminfo@foamco.com.au)